

TechNiGlove

INTERNATIONAL



RiVAL^{CR}

Accelerator Free

ORDERING INFORMATION

12" Class 100 White Soft Modulus

		Case Wt.
RVCRI500	X-SMALL	14 lbs.
RVCRI501	SMALL	17 lbs.
RVCRI502	MEDIUM	18 lbs.
RVCRI503	LARGE	18 lbs.
RVCRI504	X-LARGE	21 lbs.
RVCRI505	XX-LARGE	22 lbs.

100 Poly Bag, 10 Bags/Case = 1,000 Gloves/Case - Case Size 13"x12"x12"

PHYSICAL PROPERTIES

Style: Non-Sterile	Ambidextrous
Length:	12" (300mm)
Thickness:	4 mil (.004")
Grip Surface:	Textured Fingertips
Cuff:	Beaded
Color:	White
Tensile Strength:	14 MPa minimum
Elongation	650% minimum

TECHNICAL PROPERTIES

Particle Levels:	<2500 total particles/cm ² >0.5µm
Electrical Properties Resistivity:	≤1x10 ¹⁰ ohm/square per ESD-S11.12
Static Decay:	≤5 seconds per RETS-5-003
Total Non Volatile Residue:	5.0 µg/cm ²

Extractables

Silicone:	None	Sulfate (SO ₄ ²⁻):	<1.00 µg/cm ²
Amide:	None	Lithium (Li ⁺):	<0.05 µg/cm ²
Phthalates:	None	Sodium (Na ⁺):	<0.05 µg/cm ²
Fluoride (F ⁻):	<0.05 µg/cm ²	Ammonium (NH ₄ ⁺):	<0.05 µg/cm ²
Chloride (Cl ⁻):	<1.5 µg/cm ²	Potassium (K ⁺):	<0.05 µg/cm ²
Bromide (Br ⁻):	<0.05 µg/cm ²	Magnesium (Mg ²⁺):	<0.05 µg/cm ²
Nitrate (NO ₃ ⁻):	<1.00 µg/cm ²	Calcium (Ca ²⁺):	<0.80 µg/cm ²
Phosphate (PO ₄ ³⁻):	<0.05 µg/cm ²		
Nitrite	<0.05 µg/cm ²		

CHEMICAL RESISTANCE GUIDE

Acetic Acid	G	Isobutyl Alcohol	G
Acetone	F	Isooctane	E
Acetonitrile	F	Isopropyl Alcohol	G
Allyl Alcohol	G	Lactic Acid (85%)	E
Amyl Acetate	F	Maleic Acid	E
Amyl Alcohol	E	Methyl Alcohol	P
Butyl Alcohol	E	Methyl Amine	G
Butyl Cellosolve	E	Methyl T-Butyl Ether	P
Carbon Tetrachloride	F	Mineral Spirits	G
Citric Acid (10%)	E	Monoethanoline	E
Diacetone Alcohol	P	Naptha	F
Dibutyl Phthalate	E	Octanol	E
Dimethyl Sulfoxide	G	Oleic Acid	E
Ethyl Acetate	P	Oxalic Acid	E
Ethyl Alcohol	G	Pentachlorophenol	E
Ethyl Ether	F	Pentane	P
Ethyl Glycol Ether	G	Perchloroethylene	F
Ethylene Glycol	E	Potassium Hydroxide	E
Formaldehyde	F	Propyl Alcohol	G
Gasoline	F	Sodium Hydroxide	E
Hexane	E	Stoddard Solvent	E
Hydrazene (65%)	E	Sulfuric Acid	E
Hydrochloric Acid (10%)	E	Toluene	F
Hydrogen Peroxide (30%)	E	Turpentine	G
Hydroquinone	E	Xylene	F

E = Excellent G = Good F = Fair P = Poor

NOTE: The recommendations above are meant as a general guide when selecting gloves for any chemical contact use. TechNiTrile nitrile gloves are dipped thin for dexterity and comfort. The trade-off in emphasizing these qualities is the fact that the gloves provide only a limited degree of chemical "splash" protection. They do not provide the high degree of chemical protection found in heavier weight gloves designed specifically for chemical use.

TechNiGlove
INTERNATIONAL

1220 Graphite Drive • Corona, CA 92881 • USA

Toll Free: 1-877-648-745

Phone: 951-582-0890

Fax: 951-582-0990

Visit us on the web at www.Techniglove.com